



PRODUCT DATA SHEET

PROD. #1011

RUST SHIELD INDUSTRIAL

POLYURETHANE ALUMINUM COATING



PRODUCT DESCRIPTION

Rust Shield Industrial Polyurethane Aluminum Coating is a quality resin based aluminum protective coating designed to meet the strictest durability requirements of the industrial maintenance market. Its special formulation exhibits a brilliant silver aluminum finish for superior reflectivity. It provides superior weather resistance on substrates that have a specific need for application of an aluminum coating. Its ease of application spreads easily and has excellent leveling properties. It provides superior durability, moisture resistance, excellent coverage, excellent adhesion, and its rust inhibitive properties serve to protect a variety of metal surfaces. Its bright aluminum gloss finish also reflects ultra-violet rays, thus reducing heat. Meets MPI Standard #1 of the Master Painters Institute's approved products list.



MEETS MPI STANDARD #1 OF THE MASTER PAINTERS INSTITUTE'S APPROVED PRODUCTS LIST.

PRODUCT FEATURES	PRODUCT USES	PERFORMANCE QUALITIES	VOC COMPLIANCE																												
<ul style="list-style-type: none"> Bright Aluminum Finish Rust Inhibitive Excellent Durability Excellent Weather Resistant Outstanding Reflectivity Superior Moisture Resistance Easy To Apply 	<p>Suitable for the following properly prepared surfaces;</p> <p>INTERIOR / EXTERIOR METAL</p> <table> <tr> <td>Doors</td> <td>Machinery</td> </tr> <tr> <td>Tanks</td> <td>Tractors</td> </tr> <tr> <td>Roofs</td> <td>Silos</td> </tr> <tr> <td>Appliances</td> <td>Ferrous Metal</td> </tr> <tr> <td>Chain Link Fence</td> <td>Non-Ferrous Metal</td> </tr> </table> <p>NOTE: For Use On Metal Surfaces Only! For Interior & Exterior Use!</p>	Doors	Machinery	Tanks	Tractors	Roofs	Silos	Appliances	Ferrous Metal	Chain Link Fence	Non-Ferrous Metal	<p>Product Quality: Professional / Best</p> <p>Product Use: Interior / Exterior</p> <p>Application: Brush, Roller Cover, Airless Spray</p> <p>Product System: Solvent-Based</p> <p>Finish: N/A</p>	<table> <tr> <td>AIM</td> <td>Yes</td> </tr> <tr> <td>OTC</td> <td>Yes</td> </tr> <tr> <td>CARB</td> <td>Yes</td> </tr> <tr> <td>SCAQMD</td> <td>Yes</td> </tr> <tr> <td>MPI #</td> <td>1</td> </tr> <tr> <td>LEED® 09CI</td> <td>No</td> </tr> <tr> <td>LEED® 09NC</td> <td>No</td> </tr> <tr> <td>LEED® 09CS</td> <td>No</td> </tr> <tr> <td>LEED® H</td> <td>No</td> </tr> </table>	AIM	Yes	OTC	Yes	CARB	Yes	SCAQMD	Yes	MPI #	1	LEED® 09CI	No	LEED® 09NC	No	LEED® 09CS	No	LEED® H	No
Doors	Machinery																														
Tanks	Tractors																														
Roofs	Silos																														
Appliances	Ferrous Metal																														
Chain Link Fence	Non-Ferrous Metal																														
AIM	Yes																														
OTC	Yes																														
CARB	Yes																														
SCAQMD	Yes																														
MPI #	1																														
LEED® 09CI	No																														
LEED® 09NC	No																														
LEED® 09CS	No																														
LEED® H	No																														

SURFACE PREPARATION

General: The entire surface area to be painted should be clean, dry, sound, and free from dirt, grease, oils, waxes, mildew and any other surface contaminants that may adversely affect the performance of this coating material as follows;

- Previously Painted Metal:** Remove any loose, scaling, cracked or peeling paint from previously painted surfaces by hand scraping, sanding, wire brushing or by power tool cleaning methods, such as electric sanders or grinders, etc.
- Sand all rough paint edges smooth to adjacent surface area. Sand all glossy surfaces effectively to dull existing finish.
- Bare Metal:** Surfaces should be solvent cleaned in accordance with SSPC-SP 1 specifications pertaining to surface preparation for the solvent cleaning of steel and metal surfaces for removing all visible oil, grease, soil, drawing and cutting compounds and other soluble contaminants from the surface.
- Remove any loose rust, mill scale, rust deposits, or white rust by hand scraping, sanding, or wire brush cleaning in accordance with SSPC-SP 2 specifications pertaining to hand tool cleaning, or SSPC-SP 3 specifications pertaining to power tool cleaning of loose, non-adherent material on metal surfaces as set forth by the Steel Structures Painting Council.
- Repair/replace any damaged and/or delaminated surface areas with the proper building materials.
- Prime and/or spot prime all bare or new metal surface areas with Manufacturer's properly specified primer/sealer compatible to the surface type and before application of finish coating.

Mildew - Surface areas affected by mildew should be treated with a commercial mildew removal and/or wash product carefully following manufacturer's application and safety directions. Rinse thoroughly with clean water, and allow a minimum of 24 hours to dry thoroughly.

- WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how you can protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-Lead, or log onto www.epa.gov/lead.

PRODUCT ANALYSIS DATA

PIGMENT: 10.85%

VEHICLE: 89.15%

MORE DETAILED PRODUCT ANALYSIS DATA IS AVAILABLE UPON REQUEST.

TECHNICAL DATA

- COLORS:** Bright Aluminum
- TINTING:** Not Recommended
- VEHICLE TYPE:** Alkyd/Urethane
- VISCOSITY:** 27 – 30 Sec. / #2 Zahn Cup
- GLOSS @ 60°:** N/A
- FLASH POINT:** 107° F
- VOC:** Not to Exceed 500 g/l – 4.20 lb/gal. (Meets AIM, OTC, CARB & SCAQMD Standards)
- SOLIDS:** By Volume: 44.50% ± 2%
By Weight: 51.10% ± 2%
- COVERAGE:** 300 – 400 Sq. Ft. / Gal. (Depending on Application & Surface Porosity.)
- MIL FILM:** Estimated @ 350 Sq. Ft. / Gal.
Wet: 4.0 mils
Dry: 2.0 mils
- DRY TIME:** (@ 70° F & 50% Relative Humidity)
To Touch: 4 – 6 Hours
Recoat: Overnight
- CLEAN UP:** Mineral Spirits
- THINNING:** DO NOT THIN!

RECOMMENDED PRIMER COATINGS

The following Richard's products are recommended primer coatings for this finish coating material. However, recommended Richard's primer coatings are not limited to the products listed below;

- **Ferrous or Non-Ferrous:**
 - 1018, Rust Shield Rust Inhibitive White Metal Primer
 - 1120, Industrial Coatings White Universal Primer
 - 2215 / 2220, Industrial Epoxy Gray / White Primers
- **Galvanized or Zinc Coated Metal:**
 - 7-44, PPS 100% Acrylic Universal Primer/Sealer
 - 1017, Rust Shield Zinc Chromate Metal Primer
 - 1215 / 1220 Rust Shield II Acrylic DTM Gray / White Metal Primers
- **Previously Painted Surfaces:**
 - Self-Priming

APPLICATION EQUIPMENT

- **Brush Application:** Apply using quality nylon, polyester or combination nylon/polyester, or a quality natural china bristle brush.
- **Roller Application:** Apply using a smooth - medium nap synthetic, lamb's wool or mohair roller cover, depending on texture or surface porosity.
- **Spray Application:**
 - **Pump:** Gas or Electric Airless Sprayer
 - **Pressure:** Minimum 1500 – 2000 PSI
 - **Tip:** 0.013 – 0.017 Reversible
 - **Hose:** ¼ inch (6.3 mm) - ¾ inch (10 mm)

PACKAGING & WEIGHT PER GALLON

- **Packaging:**

Quarts – 6/case	Gallons – 4/case
2 Gallons – N/A	5 Gallons - Each
- **Weight Per Gallon:** 8.31 lbs.

CLEAN UP & THINNING INSTRUCTIONS

Clean Up: Clean up any minor spills and splatters immediately with **Mineral Spirits**, as well as all painting tools and airless equipment. More serious spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Thinning: Stir thoroughly and apply as it comes from the container. Thinning is not necessary. However, if thinning is required, you may add **Mineral Spirits**.

WARRANTY & LIMITATIONS

The technical information contained herein is accurate to the best of our knowledge. All warranties are excluded, whether expressed or implied, by operation of law or otherwise, including all implied warranties of merchantability or fitness for a particular purpose. Seller shall not be liable, directly or indirectly, under any circumstances for consequential, incidental, special or any other type of damages arising or resulting for any reason under the sale, handling, or use of goods sold. Seller's liability hereunder, and buyer's exclusive remedy hereunder, for negligence or any other reason, is expressly limited to reimbursement of the purchase price of the materials sold after proof of purchase is provided to the seller. Notice of any alleged failure or defect in the material must be given to the seller in writing by certified U.S. mail within 15 days of noticing the problem. Failure to give the required notice within the time provided constitutes a waiver of any claim. The Manufacturer is not responsible for any misrepresentation made by the Dealer.

REV 06-13

PRODUCT APPLICATION – General

Rust Shield Industrial Polyurethane Aluminum Coating may be easily applied with a quality brush, roller cover, or airless spray equipment as follows;

- Stir thoroughly in a spiral up and down motion before and during application to keep product completely mixed.
- For best results, it is recommended to apply two (2) finish coats.
- Always paint to a natural break in the surface, such as a corner or edge.
- When applying by brush, apply a smooth and generous coat on smaller surface areas, such as cutting-in larger surfaces and painting trim.
- When applying by roller cover, apply an even and generous coat in a “W” or crisscross motion, avoiding any excessive respreading or reworking.
- When applying by airless spray equipment, use a unit with a minimum of 2000 psi of pressure, with a 0.013 – 0.017 fluid spray tip.
- During spray application, it is recommended to back-roll the surface area to ensure proper adhesion, an even coat application.
- Maintain a wet edge during application by brushing, rolling or spraying into previously applied coating area.
- Apply when surface and ambient temperatures are above 55° F and below 90° F.
- Avoid exterior paint application when weather conditions are threatening, and late in the day when there is a threat of moisture condensing on wet paint.

SPECIAL NOTE: Do Not Shake This Product In A Mechanical Shaker, As It May Cause Gassing Of The Product And Build Up Excessive Pressure In The Container!

PRODUCT LIMITATIONS

- For use on metal surfaces only.
- Not for use in corrosive or chemical environments.
- Not for use in areas subject to intense heat.
- Not for use on below grade substrates.

PRECAUTIONARY & SAFETY INFORMATION

CAUTIONS: COMBUSTIBLE! KEEP OUT OF REACH OF CHILDREN! Keep away from heat, sparks and open flames. **INSURE PROPER CROSS-VENTILATION UNTIL COATING HAS DRIED!** Where ventilation is inadequate, use a suitable respirator. Turn off main gas valve until after coating has dried, then have pilot lights re-lighted by a responsible person. Avoid prolonged contact with skin and breathing of vapors and/or spray mists. When spraying this material, use an **OSHA** approved cartridge respirator. Use chemical safety glasses, goggles, or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking. Close container after each use. **DO NOT TAKE INTERNALLY!**

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soapy water. For eye contact, flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting, get medical attention immediately.

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents herein may be harmful or fatal.

KEEP OUT OF REACH OF CHILDREN!