



PRODUCT DATA SHEET

PROD. #730 SERIES
SIGNATURE SERIES
INTERIOR ALKYD EGGSHELL ENAMEL



PRODUCT DESCRIPTION

Signature Series Alkyd Eggshell Enamel is our finest quality alkyd eggshell enamel coating formulated for application to a variety of interior metal surfaces. It provides excellent coverage, offers exceptional leveling properties for a smooth finish, provides excellent durability and performance, and is easy to apply. Its soft eggshell finish resists abrasion, provides superior chemical resistance, resists sagging and yellowing, is an excellent rust preventative coating, and offers excellent product versatility.

PRODUCT FEATURES	PRODUCT USES	PERFORMANCE QUALITIES	VOC COMPLIANCE																														
<ul style="list-style-type: none"> Premium Quality Soft Eggshell Finish Rust Preventative Formula Superior Coverage Abrasion & Mar Resistant Excellent Durability Resists Sagging Excellent Leveling Qualities Easy To Use 	<p>Suitable for the following properly prepared surfaces:</p> <p>INTERIOR METAL</p> <table> <tr> <td>Doors</td> <td>Machinery</td> </tr> <tr> <td>Trim</td> <td>Furniture</td> </tr> <tr> <td>Appliances</td> <td>Ferrous Metal</td> </tr> <tr> <td>Piping</td> <td>Non-Ferrous Metal</td> </tr> <tr> <td>Tools</td> <td>Aluminum</td> </tr> <tr> <td>Equipment</td> <td>Galvanized Metal</td> </tr> </table> <p>NOTE: For Use On Metal Surfaces Only! For Interior Use Only!</p>	Doors	Machinery	Trim	Furniture	Appliances	Ferrous Metal	Piping	Non-Ferrous Metal	Tools	Aluminum	Equipment	Galvanized Metal	<p>Product Quality: Premium / Best</p> <p>Product Use: Interior</p> <p>Application: Brush, Roller Cover, Airless Spray</p> <p>Product System: Solvent-Based</p> <p>Finish: Eggshell</p>	<table> <tr> <td>AIM</td> <td>Yes</td> </tr> <tr> <td>OTC</td> <td>Yes</td> </tr> <tr> <td>CARB</td> <td>No</td> </tr> <tr> <td>SCAQMD</td> <td>No</td> </tr> <tr> <td>MPI #</td> <td>No</td> </tr> <tr> <td>LEED® 09CI</td> <td>No</td> </tr> <tr> <td>LEED® 09NC</td> <td>No</td> </tr> <tr> <td>LEED® 09CS</td> <td>No</td> </tr> <tr> <td>LEED® H</td> <td>No</td> </tr> </table>	AIM	Yes	OTC	Yes	CARB	No	SCAQMD	No	MPI #	No	LEED® 09CI	No	LEED® 09NC	No	LEED® 09CS	No	LEED® H	No
Doors	Machinery																																
Trim	Furniture																																
Appliances	Ferrous Metal																																
Piping	Non-Ferrous Metal																																
Tools	Aluminum																																
Equipment	Galvanized Metal																																
AIM	Yes																																
OTC	Yes																																
CARB	No																																
SCAQMD	No																																
MPI #	No																																
LEED® 09CI	No																																
LEED® 09NC	No																																
LEED® 09CS	No																																
LEED® H	No																																

SURFACE PREPARATION

General: The entire surface area to be painted should be clean, dry, sound, and free from dirt, grease, oils, waxes, mildew and any other surface contaminants that may adversely affect the performance of this coating material.

- Remove any loose, scaling, cracked or peeling paint from previously painted surfaces by hand scraping, sanding, wire brushing or by power tool cleaning methods, such as electric sanders or grinders, etc.
- For metal surfaces, remove any loose rust, mill scale, rust deposits or white rust from metal surface by the same methods as described above.
- Repair/replace any damaged and/or delaminated surface areas with the proper patching and/or building materials. Allow all patching materials to dry thoroughly before application of paint coatings.
- Sand all rough paint edges smooth to adjacent surface area. Sand all glossy surfaces effectively to dull existing finish.
- Prime or spot prime all bare and/or new surface areas with Manufacturer's properly specified primer/sealer compatible to the surface type and before application of finish coating.

Mildew - Surface areas affected by mildew should be treated with a commercial mildew removal and/or wash product carefully following manufacturer's application and safety directions. Rinse thoroughly with clean water, and allow a minimum of 24 hours to dry thoroughly.

- WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how you can protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-Lead, or log onto www.epa.gov/lead.

PRODUCT ANALYSIS DATA

PIGMENT: 44.54%

VEHICLE: 55.46%

MORE DETAILED PRODUCT ANALYSIS DATA IS AVAILABLE UPON REQUEST.

TECHNICAL DATA

- COLORS:** White & Tint Bases

730 – White	731 – Tint Base
732 – Deep Base	733-A – Accent Base
- TINTING:** Universal Colorants
- VEHICLE TYPE:** Alkyd
- VISCOSITY:** 87 KU ± 2
- GLOSS @ 60°:** Eggshell / 30 - 40 units ± 2
- FLASH POINT:** 103° F
- VOC:** Not to Exceed 400 g/l – 3.36 lb/gal
(Meets AIM & OTC Standards)
- SOLIDS:** By Volume: 53.57% ± 2%
By Weight: 70.98% ± 2%
- COVERAGE:** 300 – 400 Sq. Ft. / Gal.
(Coverage will vary significantly depending on application method, surface porosity and condition of the surface.)
- MIL FILM:** Estimated @ 350 Sq. Ft. / Gal.
Wet: 4.6 mils **Dry:** 2.5 mils
- DRY TIME:** (@ 70° F & 50% Relative Humidity)
To Touch: 4 – 6 Hours
Recoat: Overnight
(Dry times listed may vary according to relative humidity, temperature, film build, color and air movement.)
- CLEAN UP:** Mineral Spirits
- THINNING:** Do Not Thin!

RECOMMENDED PRIMER COATINGS

The following Richard's products are recommended primer coatings for this finish coating material. However, recommended Richard's primer coatings are not limited to the products listed below;

- **Ferrous or Non-Ferrous:**
 - 1015, Rust Shield Red Oxide Rust Inhibitive Metal Primer
 - 1018, Rust Shield Rust Inhibitive White Metal Primer
 - 1120, Industrial Coatings White Universal Primer
 - SR-933, Painter's Pride Professional Coatings Alkyd Primer/Sealer
- **Galvanized or Zinc Coated Metal:**
 - 26, Holzout II 100% Acrylic Primer/Sealer Stain Killer
 - 1017, Rust Shield Zinc Chromate Metal Primer
 - 1215 / 1220 Rust Shield II Acrylic DTM Gray / White Metal Primers
- **Previously Painted Surfaces:**
 - Self-Priming

APPLICATION EQUIPMENT

- **Brush Application:** Apply using quality nylon, polyester or combination nylon/polyester, or a quality natural china bristle brush.
- **Roller Application:** Apply using a smooth - medium nap synthetic, lamb's wool or mohair roller cover, depending on texture or surface porosity.
- **Spray Application:**
 - **Pump:** Gas or Electric Airless Sprayer
 - **Pressure:** Minimum 1500 – 2000 PSI
 - **Tip:** 0.013 – 0.015 Reversible
 - **Hose:** ¼ inch (6.3 mm) - ⅜ inch (10 mm)

PACKAGING & WEIGHT PER GALLON

- **Packaging:** Quarts – 6/case Gallons – 4/case
2 Gallons – N/A 5 Gallons – N/A
- **Weight Per Gallon:** 11.00 lbs.

CLEAN UP & THINNING INSTRUCTIONS

Clean Up: Clean up any minor spills and splatters immediately with **Mineral Spirits**, as well as all painting tools and airless equipment. More serious paint spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Thinning: Stir thoroughly and apply as it comes from the container. Thinning is not necessary. However, if thinning is required, you may add **Mineral Spirits**.

WARRANTY & LIMITATIONS

The technical information contained herein is accurate to the best of our knowledge. All warranties are excluded, whether expressed or implied, by operation of law or otherwise, including all implied warranties of merchantability or fitness for a particular purpose. Seller shall not be liable, directly or indirectly, under any circumstances for consequential, incidental, special or any other type of damages arising or resulting for any reason under the sale, handling, or use of goods sold. Seller's liability hereunder, and buyer's exclusive remedy hereunder, for negligence or any other reason, is expressly limited to reimbursement of the purchase price of the materials sold after proof of purchase is provided to the seller. Notice of any alleged failure or defect in the material must be given to the seller in writing by certified U.S. mail within 15 days of noticing the problem. Failure to give the required notice within the time provided constitutes a waiver of any claim. The Manufacturer is not responsible for any misrepresentation made by the Dealer.

REV 08-14

PRODUCT APPLICATION – General

Signature Series Alkyd Eggshell Enamel may be easily applied with a quality brush, roller cover, or airless spray equipment as follows;

- Stir thoroughly in a spiral up and down motion before and during application to keep product completely mixed.
- For best results, it is recommended to apply two finish coats.
- To assure color uniformity always intermix multiple containers of custom tinted and stock colors. Apply a small test sample to verify color.
- Always paint to a natural break in the surface, such as a corner or edge.
- When applying by brush, apply a smooth and generous coat on smaller surface areas, such as cutting-in larger surfaces and painting trim.
- When applying by roller cover, apply an even and generous coat in a "W" or crisscross motion, avoiding any excessive respraying or reworking.
- When applying by airless spray equipment, use a unit with a minimum of 2000 psi of pressure, with a 0.013 – 0.015 fluid spray tip.
- During spray application, it is recommended to back-roll the surface area to ensure proper adhesion, and an even coat application.
- Maintain a wet edge during application by brushing, rolling or spraying into previously applied coating area.
- Apply when surface and ambient temperatures are above 55° F and below 90° F.

PRODUCT LIMITATIONS

- Not for exterior application.
- Not for use in corrosive or chemical environments.
- Not for use in areas subject to intense heat.
- Not for use on below grade substrates.

PRECAUTIONARY & SAFETY INFORMATION

CAUTIONS: COMBUSTIBLE! KEEP OUT OF REACH OF CHILDREN! Keep away from heat, sparks and open flames. **INSURE PROPER CROSS-VENTILATION UNTIL COATING HAS DRIED!** Where ventilation is inadequate, use a suitable respirator. Turn off main gas valve until after coating has dried, then have pilot lights re-lighted by a responsible person. Avoid prolonged contact with skin and breathing of vapors and/or spray mists. When spraying this material, use an **OSHA** approved cartridge respirator. Use chemical safety glasses, goggles, or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking. Close container after each use. **DO NOT TAKE INTERNALLY!**

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soapy water. For eye contact, flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting, get medical attention immediately.

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents herein may be harmful or fatal.

KEEP OUT OF REACH OF CHILDREN!