



PRODUCT DATA SHEET

PROD. 57500.0

PAINTER'S PRIDE PROFESSIONAL COATINGS

ALKYD FLAT INDUSTRIAL MAINTENANCE COATING



PRODUCT DESCRIPTION

Richard's Painter's Pride Alkyd Flat Industrial Maintenance Coating is a premium professional grade, heavy-bodied interior alkyd flat rust preventative finish paint designed for application to a variety of metal surfaces. Specially formulated for use by the professional painting contractor, it applies easily, provides excellent coverage, touch-up properties and superior durability. It is self-priming, alkali resistant, and has superior leveling properties. Its smooth flat glare free enamel hard finish is ideally suited to meet performance requirements in primarily commercial and industrial maintenance venues, such as hotels, motels, warehouses, apartments, office buildings, etc. **For Use On Metal Surfaces Only**

PRODUCT FEATURES	PRODUCT USES	PERFORMANCE QUALITIES
- Professional Quality - Smooth Flat Finish - Excellent Coverage - Excellent Touch-Up Properties - Superior Durability - Self-Priming - Excellent Leveling - Excellent Product Versatility	<i>Suitable for, but not limited to the following properly prepared surfaces:</i> INTERIOR METAL - Doors - Trim - Appliances - Piping - Tools - Equipment - Machinery - Furniture - Ferrous Metal - Non-Ferrous Metal - Aluminum - Galvanized Metal NOTE: For Use On Metal Surfaces Only Great For Interior & Exterior Use	Product Quality: Professional Product Use: Interior / Exterior Application: Brush, Roller, Airless Spray Product System: Solvent-Based Sheen: Flat MPI Standards: No VOC Compliance: EPA AIM, LADCO, OTC Phase I

SURFACE PREPARATION

GENERAL: The entire surface area to be painted should be clean, dry, sound, and free from dirt, grease, oils, waxes, mildew and any other surface contaminants that may adversely affect the performance of this coating material.

- PREVIOUSLY PAINTED METAL SURFACES:** Remove any loose, scaling, cracked or peeling paint from previously painted surfaces by hand scraping, sanding, wire brushing or by power tool cleaning methods, such as electric sanders or grinders, etc. Remove any loose rust, mill scale, rust deposits or white rust from metal surface by the same methods as described above. Sand all rough paint edges smooth to adjacent surface area. Sand all glossy surfaces to dull existing finish. Spot prime all bare surface areas with same primer material and allow to thoroughly dry before applying finish coatings.
- SURFACE REPAIRS:** Repair/replace any damaged and/or delaminated surface areas with the proper recommended patching and/or building materials. Allow patching materials to dry thoroughly before application of paint coatings
- METAL SURFACES:** For metal surfaces, remove any loose rust, mill scale, rust deposits or white rust from metal surface in accordance with SSPC-SP 2 – Hand Tool Cleaning specifications, or by power tool cleaning methods, such as electric sanders or grinders according to SSPC-SP 3 – Power Tool Cleaning specifications, as set forth by The Society for Protective Coatings. Previously painted surfaces, whereby the existing paint show signs of serious deterioration should be completely removed in accordance with SSPC-SP 6 – Commercial Blast Cleaning, or SSPC-SP 10 – Near White Blast Cleaning specifications.
- MILDEW:** Surface areas affected by mildew should be treated with a commercial mildew removal and/or wash product carefully following manufacturer's application and safety directions. Rinse thoroughly with clean water, and allow a minimum of 24 hours to dry thoroughly.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how you can protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-Lead, or log onto www.epa.gov/lead.

TECHNICAL DATA

- COLORS:** White Only
- TINTING:** Universal Colorants – (Pastel Colors Only)
- VEHICLE TYPE:** Alkyd
- VISCOSITY:** 102 KU $\pm$ 3
- GLOSS @ 60°:** Flat | 0-5 units
- FLASH POINT:** 107° F
- COATING VOC:** Not to Exceed 400 g/l – 3.36 lbs./gal
(Meets EPA AIM, LADCO, OTC Phase I Standards)
- SOLIDS BY VOLUME:** 51.96% $\pm$ 2%
- SOLIDS BY WEIGHT:** 76.69% $\pm$ 2%
- ESTIMATED COVERAGE:** 300 – 400 SFPG
(Coverage will vary significantly depending on application method, surface porosity and condition of the surface.)
- RECOMMENDED MIL FILM:** (Estimated @ 350 SFPG)
Wet: 4.6 mils **Dry:** 3.2 mils
- ESTIMATED DRY TIME:** (@ 70° F & 50% Relative Humidity)
To Touch: 2 hrs. | **Recoat:** 4 – 6 hrs. or overnight
(Actual dry time may vary according to relative humidity, temperature, color, applied film build and air movement.)
- DRIES BY:** Oxidation / Solvent Evaporation
- CLEAN UP:** Mineral Spirits
- THINNING:** Not Recommended
- WEIGHT/GAL:** 13.65 lbs.
- SHELF LIFE:** 2 - 3 years unopened.
- PACKAGING:** | Gal. – 4/cs. | 5 Gal. - Each

RECOMMENDED PRIMER COATINGS

Although formulated to be self-priming on sound and properly prepared painted surfaces, the following Richard's primers are recommended for use on new or bare substrates;

Ferrous or Non-Ferrous:

- 1000.121 - Rust Shield Red Oxide Rust Inhibitive Metal Primer
- 1000.101 - Rust Shield Rust Inhibitive White Metal Primer
- 1120.101 - Industrial Coatings White Universal Primer
- 933.101 - Painter's Pride Professional Coatings Alkyd Primer/Sealer

Galvanized or Zinc Coated Metal:

- 26.101 - HOLZOUT 100% Acrylic Universal Primer/Sealer
- 36.101 - HOLZON Waterborne Bonding Primer
- 1200.111 - EXCEL Acrylic DTM Gray Metal Primer
- 1200.101 - EXCEL Acrylic DTM White Metal Primers
- 1200.30 - EXCEL Waterborne Bonding Primer

Previously Painted Surfaces:

- Self-Priming

APPLICATION EQUIPMENT

Brush Application: Apply using quality nylon, polyester or combination nylon/polyester, or a quality natural china bristle brush.

Roller Application: Apply using a smooth - medium nap synthetic, lamb's wool or mohair roller cover, depending on texture or surface porosity.

Spray Application:

- **Pump:** Gas or Electric Airless Sprayer
- **Pressure:** Minimum 2000 PSI
- **Tip:** 0.015 – 0.017 Reversible
- **Hose:** ¼ inch (6.3 mm) - ¾ inch (10 mm)

PRODUCT LIMITATIONS

- Not for use in corrosive or chemical environments.
- Not for use in areas subject to intense heat.
- Not for use on below grade substrates.

CLEAN UP & THINNING INSTRUCTIONS

Clean Up: Clean up any minor spills and spatters immediately with **Mineral Spirits**, as well as all painting tools and airless equipment. More serious spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Thinning: Stir thoroughly and apply as it comes from the container. Thinning is not necessary. However, if thinning is required, you may add **Mineral Spirits**.

PRODUCT APPLICATION – General

Richard's Painter's Pride Alkyd Flat Industrial Maintenance Coating may be easily applied with a quality brush, roller, or spray equipment as follows;

- Stir thoroughly in a spiral up and down motion before and during application to keep product completely mixed.
- For best results, it is recommended to apply two (2) finish coats.
- To assure color uniformity always intermix multiple containers of custom tinted and stock colors. Apply a small test sample to verify color.
- Always paint to a natural break in the surface, such as a corner or edge.

Brush Applications: When applying by brush, use a quality nylon or polyester bristle brush, or a quality combination of both, or a quality china bristle brush and apply a smooth and generous coat on smaller surface areas, such as cutting-in larger surfaces and painting trim.

Roller Application: When applying by roller cover, use a quality smooth, medium or rough nap roller, depending on surface porosity, and apply an even and generous coat in a "W" or crisscross motion, avoiding any excessive respraying or reworking.

Spray Application: When applying by airless spray equipment, use a unit with a minimum of 2000 psi of pressure, with a 0.015" – 0.017" spray tip.

- During spray application, it is recommended to back-roll the surface area to ensure proper adhesion, an even coat application.
- Maintain a wet edge during application by brushing, rolling or spraying into previously applied coating area.
- Apply when surface and ambient temperatures are above 55° F and below 90° F.

PRECAUTIONARY & SAFETY INFORMATION

CAUTIONS: COMBUSTIBLE! Keep away from heat, sparks and open flames. **INSURE PROPER CROSS-VENTILATION UNTIL COATING HAS DRIED!** Where ventilation is inadequate, use a suitable respirator. Turn off main gas valve until after coating has dried, then have pilot lights re-lighted by a responsible person. Avoid prolonged contact with skin and breathing of vapors and/or spray mists. When spraying this material, use an OSHA approved cartridge respirator. Use chemical safety glasses, goggles, or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking. Close container after each use. **DO NOT TAKE INTERNALLY!**

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soapy water. For eye contact, flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting, get medical attention immediately.

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents herein may be harmful or fatal.

KEEP OUT OF REACH OF CHILDREN!

LIMITED WARRANTY

Richard's Paint warrants our products to meet the application, appearance and performance properties stated on the label. This Limited Warranty shall not apply to any defect or damage resulting from improper surface preparation, structural defects, failure of a previous paint or improper application of the coating, as described in the directions on the label of this container. If this product is found not to perform as specified, Richard's Paint will, at its option and upon presentation of proof-of-purchase (the original receipt), either furnish an equivalent amount of new product or refund the original purchase price of this product to you. **ALL OTHER WARRANTIES ARE EXCLUDED BY RICHARD'S PAINT, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

LIMITATIONS

Seller's liability for any reason is expressly limited to reimbursement of the purchase price of the materials sold after proof of purchase is provided to the seller. **THIS WARRANTY EXCLUDES (1) LABOR AND COSTS ASSOCIATED WITH LABOR FOR THE APPLICATION OR REMOVAL OF ANY PRODUCT, AND (2) ANY INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES ARISING OR RESULTING FOR ANY REASON UNDER THE SALE, HANDLING, OR USE OF GOODS SOLD.** Some states do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty gives you specific legal rights and you may also have other rights, which vary from state to state. This Limited Warranty may not be transferred or assigned.

REV 04-25