



PRODUCT DATA SHEET

PROD. 9600TW – TINTING WHITE

RICH PRO 4000

ACRYLIC INTERIOR FLAT WALL PAINT



PRODUCT DESCRIPTION

Rich Pro 4000 Interior Acrylic Latex Flat Wall Paint – Tinting White is a professional quality interior latex wall coating formulated for tinting to light and pastel shades of color. Developed for use by the professional painting contractor, its special formulation provides good coverage and touch-up qualities, is self-priming, non-yellowing, durable, and is washable. Its ease of application and product versatility allows for application to a variety of interior substrates, and Rich Pro 2000 is VOC compliant.

PRODUCT FEATURES		PRODUCT USES		PERFORMANCE QUALITIES		VOC COMPLIANCE	
<ul style="list-style-type: none">Professional QualitySmooth Flat FinishSuperior CoverageSuperior Touch-UpSelf PrimingNon YellowingGood DurabilityVOC CompliantApplies Easily		<i>Suitable for, but not limited to the following properly prepared surfaces;</i> INTERIOR <div><div>Gypsum DrywallMasonry</div><div>PlasterCMU Walls</div><div>CeilingsWood Trim</div><div>Primed Metal</div></div> For Interior Use Only		Product Quality:	Professional / Better	EPA AIM	Yes
				Product Use:	Interior Only	OTC	Yes
				Application:	Brush, Roller Cover, Airless Spray	CARB	Yes
				Product System:	Water-Based	SCAQMD	Yes
				Finish:	Flat	MPI #	No

SURFACE PREPARATION

General: The entire surface area to be painted should be clean, dry, sound, and free from dirt, grease, oils, waxes, mildew, rust, efflorescence, and any other surface contaminants that may adversely affect the performance of this coating material.

- Remove any loose, scaling, cracked, blistering and peeling paint from previously painted surfaces, as well as loose rust, mil scale or white rust from metal surfaces by hand scraping, sanding, wire brushing, or by power tool cleaning methods, such as electric sanders, grinders, etc.
- Repair/replace any damaged and/or delaminated surface areas such as, nail holes, gouges, cracks, etc. with the properly recommended patching compounds. Allow all patch compounds to dry thoroughly before paint application.
- Sand smooth all rough paint edges and surface repairs to adjacent main surface area.
- To effectively dull existing sheen levels, sand all glossy surfaces.
- Prime and/or spot prime all bare and/or new surface areas with the Manufacturer's properly specified primer/sealers compatible to the surface type before application of finish coating.

NOTE: Allow all new concrete and masonry substrates to dry/cure for a minimum of 30 days before application of any paint coating, and in accordance with industry standards.

Mildew - Surface areas affected by mildew should be washed with a commercial mildew removal product carefully following manufacturer's application and safety directions. Rinse thoroughly with clean water, and allow a minimum of 24 hours to dry thoroughly.

- WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how you can protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-Lead, or log onto www.epa.gov/lead.

PRODUCT ANALYSIS DATA

PIGMENT: 33.25%

VEHICLE: 66.75%

MORE DETAILED PRODUCT ANALYSIS DATA IS AVAILABLE UPON REQUEST.

TECHNICAL DATA

- COLORS:** Tinting White
- TINTING:** Universal 888 Colorant
- VEHICLE TYPE:** Proprietary Latex Acrylic
- VISCOSITY:** 103 KU \pm 2
- GLOSS @ 60°:** Flat / 0 - 5 units
- FLASH POINT:** N/A
- VOC:** Not to Exceed 50 g/l – 0.42 lb/gal
(Compliant In All Areas In the U.S and Canada)
- SOLIDS:** By Volume: 32.80% \pm 2%
By Weight: 47.53% \pm 2%
- COVERAGE:** 300 – 400 Sq. Ft. / Gal.
(Coverage will vary significantly depending on application method, surface porosity and condition of the surface.)
- MIL FILM:** Estimated @ 350 Sq. Ft. / Gal.
Wet: 4.6 mils **Dry:** 1.3 mils
- DRY TIME:** (@ 70° F & 50% Relative Humidity)
To Touch: 1 – 2 Hours
Recoat: 4 – 6 Hours, or after overnight.
(Dry times listed may vary according to relative humidity, temperature, film build, color and air movement.)
- CLEAN UP:** Warm Soapy Water
- THINNING:** Clean Water

RECOMMENDED PRIMER COATINGS

Although formulated to be self-priming on previously painted surfaces in good condition, the following Richard's products are recommended primer coatings for this finish coating material. However, recommended Richard's primer coatings are not limited to the products listed below.

New Gypsum Drywall / Plaster:

- 26.101 - HOLZOUT 100% Acrylic Primer/Sealer Stain Killer
- 711.101 - HOLZTITE Latex Primer/Sealer Undercoater
- 722.101 - HOLZTITE Universal Alkyd Primer/Sealer Undercoater

New Wood:

- 26.101 - EXCEL 100% Acrylic Primer/Sealer Stain Killer
- 722.101 - HOLZTITE Universal Alkyd Primer/Sealer Undercoater

New Masonry:

- 151A.101 - Painter's Pride Latex Masonry Airless Block Filler
- 1414.101 - Rich Flex Alkali Resistant Masonry Primer

Previously Painted Surfaces:

- Self-Priming
- 26.101 - HOLZOUT 100% Acrylic Primer/Sealer Stain Killer

APPLICATION EQUIPMENT

Brush Application: Apply using a quality nylon, polyester, or combination nylon/polyester bristle brush.

Roller Application: Apply using a ¾" - 1¼" nap synthetic or lamb's wool roller cover, depending on the texture and surface porosity.

Spray Application:

- **Pump:** Gas or Electric Airless Sprayer
- **Pressure:** Minimum 1500 – 2000 PSI
- **Tip:** 0.017 – 0.019 Reversible
- **Hose:** ¼ inch (6.3 mm) - ¾ inch (10 mm)

PACKAGING & WEIGHT PER GALLON

Packaging: Gallons – 4/case
5 Gallons - Each

Weight per Gallon: 10.70 lbs.

CLEAN UP & THINNING INSTRUCTIONS

Clean Up: Clean up any minor spills and splatters immediately with warm soapy water, as well as all painting tools and airless equipment. More serious paint spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Thinning: Stir thoroughly and apply as it comes from the container. Thinning is not necessary. However, if thinning is required, you may add clean water up to ½ pint per gallon.

PRODUCT APPLICATION – General

Richard's Rich Pro 4000 Acrylic Interior Flat Wall Paint – Tinting White may be easily applied with a quality brush, roller cover, or airless spray equipment as follows;

- Stir thoroughly in a spiral up and down motion before and during application to keep product completely mixed.
- For best results, it is recommended to apply two (2) finish coats.
- To assure color uniformity always intermix multiple containers of custom tinted and stock colors. Apply a small test sample to verify color.
- Always paint to a natural break in the surface, such as a corner or edge.
- When applying by brush, apply a smooth and generous coat on smaller surface areas, such as cutting-in larger surfaces and painting trim.
- When applying by roller cover, apply an even and generous coat in a "W" or crisscross motion, avoiding any excessive resreading or reworking.
- When applying by airless spray equipment, use a unit with a minimum of 2000 psi of pressure, with a 0.017 – 0.019 spray tip.
- During spray application, it is recommended to back-roll the surface area to ensure proper adhesion, an even coat application.
- Maintain a wet edge during application by brushing, rolling or spraying into previously applied coating area.
- If applying two finish coats, allow to dry thoroughly between coats.
- Apply when surface and ambient temperatures are above 55° F and below 90° F.

PRODUCT LIMITATIONS

- Not for use on exterior surfaces.
- Not for use in corrosive or chemical environments.
- Not for use in areas subject to intense heat.
- Not for use on below grade substrates.

PRECAUTIONARY & SAFETY INFORMATION

CAUTIONS: Avoid prolonged contact with skin, and breathing of dust, vapors and/or spray mists. Causes eye irritation. **USE WITH ADEQUATE VENTILATION!** Ensure fresh air entry during application and drying. If you experience eye water, headache or dizziness, or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriately fitted respirator, (NIOSH approved), during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Use chemical safety glasses, goggles or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking. Close container after each use. **DO NOT TAKE INTERNALLY!**

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soapy water. For eye contact, flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting, get medical attention immediately.

KEEP OUT OF REACH OF CHILDREN!

WARRANTY & LIMITATIONS

The technical information contained herein is accurate to the best of our knowledge. All warranties are excluded, whether expressed or implied, by operation of law or otherwise, including all implied warranties of merchantability or fitness for a particular purpose. Seller shall not be liable, directly or indirectly, under any circumstances for consequential, incidental, special or any other type of damages arising or resulting from any reason under the sale, handling, or use of goods sold. Seller's liability hereunder, and buyer's exclusive remedy hereunder, for negligence or any other reason, is expressly limited to reimbursement of the purchase price of the materials sold after proof of purchase is provided to the seller. Notice of any alleged failure or defect in the material must be given to the seller in writing by certified U.S. mail within 15 days of noticing the problem. Failure to give the required notice within the time provided constitutes a waiver of any claim. The Manufacturer is not responsible for any misrepresentation made by the Dealer.